

COLD ROLLED SHEET



		CHEMICAL COMPOSITION				MECHANICAL PROPERTIES
STANDARD	GRADE	C (%)	Mn (%)	P (%)	S (%)	Tensile Strength (Mpa)
SNI 07-3567-2006	Bj DC	≤0.12	≤0.50	≤0.040	≤0.045	485-620
	Bj DD 1	≤0.10	≤0.45	≤0.030	≤0.025	
	Bj DD 2	≤0.08	≤0.40	≤0.030	≤0.020	
	Bj DD 3	≤0.06	≤0.40	≤0.030	≤0.020	

In ft	3 X 6	4 X 8
In mm	914.4 X 1,829	1,219 X 2,438
0.2	2.63	4.67
0.25	3.28	5.83
0.3	3.94	7.00
0.35	4.60	8.17
0.4	5.25	9.33
0.45	5.91	10.50
0.5	6.57	11.67
0.6	7.88	14.00
0.7	9.19	16.33

In ft	3 X 6	4 X 8
In mm	914.4 X 1,829	1,219 X 2,438
0.8	10.50	18.66
0.9	11.82	21.00
1	13.13	23.33
1.1	14.44	25.66
1.2	15.76	28.00
1.3	17.07	30.33
1.4	18.38	32.66
1.5	19.70	35.00
1.6	21.01	37.33

In ft	3 X 6	4 X 8
In mm	914.4 X 1,829	1,219 X 2,438
1.8	23.63	41.99
1.9	24.95	44.33
2	26.26	46.66
2.3	30.20	53.66
2.6	34.14	60.66
2.8	36.76	65.32
3	39.39	69.99



PT. SAPTA SUMBER LANCAR
 STEEL STOCKIST, SUPPLIER AND SERVICES
 Office : Ngagel Jaya Utara no. 56, Surabaya - 60284

P : +62 31 9944 3555, +62 31 9944 3777
 F : +62 31 9944 5000
 E : sales@sapta.co